## **LG Water Solutions**







#### **Features**

- · High salt rejection
- Good fouling resistance
- Good durability

#### **Benefits**

- · High permeate water quality
- · Long-lasting, reliable performance

### **Ideal Applications**

- · Industrial process water
- · Municipal drinking water
- · Water reuse

## Product Data Sheet

# **LG BW 400 R**

High rejection brackish water RO membrane with proven, long-lasting reliability


## **Performance Specifications**

Specification	Unit	Test Condition A	Test Condition B
Permeate Flow Rate	GPD (m³/d)	10,500 (39.7)	11,000 (41.6)
Stabilized Salt Rejection	%	99.6	99.65
Minimum Salt Rejection	%	99.5	99.56
Active Membrane Area	ft² (m²)	400 (37)	
Feed Spacer Thickness	mil	34	

The specifications outlined above are based on the following test conditions:

- **Test Condition A:** 2,000 ppm NaCl, 225 psi (15.5 bar), 25°C (77°F), pH 7, Recovery 15%
- Test Condition B (referential only): 1,500 ppm NaCl, 225 psi (15.5 bar), 25°C (77°F), pH 7, Recovery 15%
- Permeate flow rates for individual elements may vary by +25/-10%

## **Dimensions and Weight**



Dimensions: mm (in)		Wet Weight: kg (lbs)	
А	В	С	
Element Length	Element O.D.	Core Tube I.D.	16 (35)
1,016 (40)	200 (7.9)	28.6 (1.125)	

## **Operating Specifications**

Item	Unit	Value
Maximum Applied Pressure	psi (bar)	600 (41.3)
Maximum Chlorine Concentration	ppm	< 0.1
Maximum Operating Temperature	°C (°F)	45 (113)
pH Range, Continuous Operation		2-11
pH Range, Cleaning		2–12
Maximum Feed Water Turbidity	NTU	1.0
Maximum Feed Water SDI <sub>15</sub>		5.0
Maximum Feed Flow	gpm (m³/h)	75 (17)
Maximum Pressure Drop (ΔP) for Each Element	psi (bar)	15 (1.0)

This product is certified to NSF/ANSI/CAN Standard 61 for drinking water systems



**Headquarter:** 54/18 Bui Quang La, Ward 12, Go Vap District, HCMC, Vietnam

**Branch office:** 77 DHT10B, Dong Hung Thuan Ward, District 12, HCMC, Vietnam

Phone: (028) 6258 5368 - (028) 6291 9568 Email: info@atswatertechnology.com Website: www.atswatertechnology.com The Membrane Elements performance is expressly conditioned on Buyer's storing, installing, operating, and maintaining Product in accordance with industry accepted good practices and Seller's written instructions provided in the Seller's Technical Manual, which consists of LG Chem, Ltd Technical Service Bulletins ("TSB") and Technical Applications Bulletins ("TAB") and may be viewed and downloaded at www.lgwatersolutions.com. The information and data contained herein are deemed to be accurate and reliable and are offered in good faith, but without guarantee of performance. LG Chem assumes no liability for results obtained or damages incurred through the application of the information contained

herein. Customer is responsible for determining whether the products and information presented herein are appropriate for the customer's use and for ensuring that customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Specifications subject to change without notice. NanoH2O is the Trademark of The LG Water Solutions or an affiliated company of LG Chem. All rights reserved. © LG Chem, Ltd.

Please visit our website for regional contact information www.lgwatersolutions.com