



Lewatit® MonoPlus M 500 MB is s strongly basic, gelular anion exchange resin with beads of uniform size (monodisperse) based on a styrene-divenylbenzene copolymer. Due to the monodisperse bead size distribution and a special manufacturing process this resin type is tailor-made for mixed bed application in make-up water systems. The resin has been optimized regarding a regeneration efficency paired with an improved rinse characteristic.

Lewatit® MonoPlus M 500 MB is especially applicable for:

» mixed bed application in combination with Lewatit® MonoPlus S 108 H

Lewatit® MonoPlus M 500 MB is adding special features to the resin bed:

- » a special bead size distribution ensuring a perfect separation of resin components without cross-contamination
- » a good utilization of the total capacity
- » a low rinse water demand
- » homogenous throughput of regenerants, water and solutions; therefore a homogenous working zone
- » sharply contrasting colours

The special properties of this product can only be fully utilized if the technology and process used correspond to the current state-of-the-art. Further advice in this matter can be obtained from Lanxess Corporation.

This document contains important information and must be read in its entirety.

Previous Edition: 2024-09-10

Edition: 2025-05-19







Common Description

Delivery form	CI ⁻
Functional group	quaternary ammonium type 1
Matrix	styrenic
Structure	gel
Appearance	yellow, translucent

Specified Data

		US Units			
Uniformity coefficient				max.	1.1
Mean bead size	d50			mm	0.62 (+-0.05)
Total capacity (delivery form)		kgr/ft³	28.4	min. eq/L	1.3

This document contains important information and must be read in its entirety.

2/5

Edition: 2025-05-19 Previous Edition: 2024-09-10







Typical Physical and Chemical Properties

		US Units		Metric Units	
Bulk density for shipment	(+/- 5%)	lb/ft³	43.1	g/L	690
Density				approx. g/mL	1.08
Water retention (delivery form)				approx. weight %	48-55
Volume change (Cl ⁻ -OH ⁻)				max. approx. %	24
Stability pH range					0-14
Storability temperature range				°C	-20 - +40

Operation

		US Units		Metric Units	
Operating temperature		max. °F	158	max. °C	70
Operating pH range	during exhaustion				0-12
Bed depth for single column		min. inches	31.5	min. mm	800
Bed depth per component in mixed bed		min. inches		min. mm	500
Back wash bed expansion per m/h (20°C)				%	11
Specific pressure loss (15°C)				kPa*h/m²	1
Max. pressure loss during operation		PSI	29	kPa	200
Specific flow rate		max. gpm/ft3	13	max. BV/h	100

Regeneration

		US Units		Metric Units	
NaOH regeneration	concentration	approx. wt. %		approx. wt. %	2-6
NaOH regeneration	quantity co-current	min. lb/ft³	6.3	min. g/L resin	100
NaOH regeneration	quantity counter- current	min. lb/ft³		min. g/L resin	50
Regeneration contact time		min. minutes		min. minutes	20
Slow rinse at regeneration flow rate		min. gal/ft³	15.0	min. BV	2
Fast rinse at service flow rate		min. gal/ft³	15.0	min. BV	2

This document contains important information and must be read in its entirety.

Edition: 2025-05-19 Previous Edition: 2024-09-10







Additional Information & Regulations

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE OF PRODUCTS MENTIONED HEREIN IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING ANY PRODUCT, ALWAYS READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION.

Safety precautions

Strong oxidants, e.g. nitric acid, can cause violent reactions if they come into contact with ion exchange resins.

Disposal

In the European Community Ion exchange resins have to be disposed, according to the European waste nomenclature which can be accessed on the internet-site of the European Union.

Storage conditions

It is recommended to store ion exchange resins at temperatures above the freezing point of water under roof in dry conditions without exposure to direct sunlight. If resin should become frozen, it should not be mechanically handled and left to thaw out gradually at ambient temperature. It must be completely thawed before handling or use. No attempt should be made to accelerate the thawing process.

Storage time

The recommended storage time for this product is explained in the technical document "Technical guidelines on the storage of Lewatit® ion exchange resins" available for download on our website. Please use the following link for more information: https://lanxess.com/en/products-and-brands/brands/lewatit/literature

Packaging

The experience has shown that the packaging stability for reliable resin containment is limited to 24 months under the storage conditions described within the product safety information. It is therefore recommended to use the product within this time frame; otherwise the packaging condition should be checked regularly.

This document contains important information and must be read in its entirety.

Previous Edition: 2024-09-10

Edition: 2025-05-19







Head Office: 54/18 Bui Quang La, An Hoi Tay Ward, HCMC, Vietnam

Branch Office:~77~Dong Hung Thuan 10B, Dong Hung Thuan Ward, HCMC, Vietnam

Phone: (028) 6258 5368 - (028) 6291 9568 Email: info@atswatertechnology.com Website: www.atswatertechnology.com

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information.

Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent.

LANXESS Corporation 111 RIDC Park West Dr 12275-1112 Pittsburgh-Allegheny USA

+1-800-678-0020 lewatit@lanxess.com

www.lanxess.com www.lpt.lanxess.com

This document contains important information and must be read in its entirety.

Edition: 2025-05-19 Previous Edition: 2024-09-10

