

Lewatit® MonoPlus M 800 KR is a strongly basic, premium grade, gel-type anion exchange resin with beads of uniform size (monodisperse), in highly regenerated and purified form to meet nuclear industry specifications.

Lewatit® nuclear resins (Lewatit® KR) are noted for their outstanding mechanical and chemical stability and their high osmotic stability.

Because of their excellent hydrodynamic properties, Lewatit® KR resins allow particularly high flow rates. The extremely high monodispersity and very low fines content result in particularly low pressure losses compared with standard resins.

Used in radioactive water circuits, they provide a number of special tasks and guarantee a water quality that fully complies with the requirements of the nuclear power industry.

Lewatit® MonoPlus M 800 KR is particularly suitable for the:

- » removal of anions, including radioactive isotopes, from aqueous solutions (including boric acid)
- » decontamination of circuits in nuclear reactor plants
- » treatment of primary coolant e.g. in pressure water reactors
- » purification of steam generator blow down irrespective of the conditioning with Levoxin (hydrazine), ethanolamine or morpholine
- » polishing in the primary and secondary sections as a mixed bed component with

Lewatit® MonoPlus SP 112 KR, Lewatit® MonoPlus S 200 KR or Lewatit® MonoPlus S 215 KR

Important!

Rinse carefully with demineralized water prior to service of mixing with **Lewatit® MonoPlus SP 112 KR, Lewatit® MonoPlus S 200 KR or Lewatit® MonoPlus S 215 KR**.

The special properties of this product can only be fully utilized if the technology and process used correspond to the current state-of-the-art. Further advice in this matter can be obtained from Lanxess Corporation.

PRODUCT INFORMATION

LEWATIT® MonoPlus M 800 KR



Common Description

Delivery form	OH ⁻
Functional group	quaternary ammonium type 1
Matrix	styrenic
Structure	gel
Appearance	light brown, translucent

Specified Data

		US Units			
Uniformity coefficient				max.	1.1
Mean bead size	d50			mm	0.64 (+/-0.05)
Total capacity (delivery form)		kgr/ft ³	26.2	min. eq/L	1.2

PRODUCT INFORMATION

LEWATIT® MonoPlus M 800 KR



Typical Physical and Chemical Properties

		US Units		Metric Units	
Bulk density for shipment	(+/- 5%)	lb/ft³	42.5	g/L	670
Density				approx. g/mL	1.07
Water retention (delivery form)				approx. weight %	56-63
Volume change (OH⁻ -Cl⁻)				max. approx. %	-22
Stability pH range					0-14
Storability temperature range				°C	-20 - +40
Friability				average g/bead	700
Friability	>200 g/bead			min. vol. %	95
Ionic conversion OH⁻				min. eq. %	95
Ionic conversion CO₃²⁻				max. eq. %	5
Ionic conversion Cl⁻				max. eq. %	0.5
Ionic conversion SO₄²⁻				max. eq. %	0.5

Operation

		US Units		Metric Units	
Operating temperature		max. °F	158	max. °C	70
Operating pH range	during exhaustion				0-12
Bed depth for single column		min. inches	31.5	min. mm	800
Bed depth per component in mixed bed		min. inches		min. mm	500
Back wash bed expansion per m/h (20°C)				%	10
Specific pressure loss (15°C)				kPa*h/m²	1
Max. pressure loss during operation		PSI	36	kPa	250
Specific flow rate		max. gpm/ft³	13	max. BV/h	100

This document contains important information and must be read in its entirety.

Trace Impurities

		Metric Units	
Na		max. mg/kg dry resin	20
Fe		max. mg/kg dry resin	30
Cu		max. mg/kg dry resin	5
Al		max. mg/kg dry resin	5
Co		max. mg/kg dry resin	5
Pb		max. mg/kg dry resin	10
Hg		max. mg/kg dry resin	5
SiO ₂		max. mg/kg dry resin	50
Total Chloride		max. mg/kg dry resin	500
SO ₄ ²⁻ as Sulphur		max. mg/kg dry resin	600

Additional Information & Regulations

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE OF PRODUCTS MENTIONED HEREIN IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING ANY PRODUCT, ALWAYS READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION.

Safety precautions

Strong oxidants, e.g. nitric acid, can cause violent reactions if they come into contact with ion exchange resins.

Disposal

In the European Community ion exchange resins have to be disposed, according to the European waste nomenclature which can be accessed on the internet-site of the European Union.

Storage conditions

It is recommended to store ion exchange resins at temperatures above the freezing point of water under roof in dry conditions without exposure to direct sunlight. If resin should become frozen, it should not be mechanically handled and left to thaw out gradually at ambient temperature. It must be completely thawed before handling or use. No attempt should be made to accelerate the thawing process.

Storage time

The recommended storage time for this product is explained in the technical document "Technical guidelines on the storage of Lewatit® ion exchange resins" available for download on our website. Please use the following link for more information: <https://lanxess.com/en/products-and-brands/brands/lewatit/literature>

Packaging

The experience has shown that the packaging stability for reliable resin containment is limited to 24 months under the storage conditions described within the product safety information. It is therefore recommended to use the product within this time frame; otherwise the packaging condition should be checked regularly.

PRODUCT INFORMATION

LEWATIT® MonoPlus M 800 KR



Head Office: 54/18 Bui Quang La, An Hoi Tay Ward, HCMC, Vietnam
Branch Office: 77 Dong Hung Thuan 10B, Dong Hung Thuan Ward, HCMC, Vietnam
Phone: (028) 6258 5368 – (028) 6291 9568
Email: info@atswatertechnology.com
Website: www.atswatertechnology.com

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information.

Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent.

LANXESS Corporation
111 RIDC Park West Dr
12275-1112 Pittsburgh-Allegheny
USA

+1-800-678-0020
lewatit@lanxess.com

www.lanxess.com
www.lpt.lanxess.com

This document contains important information and must be read in its entirety.

Edition: 2025-05-19
Previous Edition: 2024-11-05